

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Hunter Douglas Limited
338 Victoria Road
Rydalmere NSW 2116

Test Number : 24-004243
Issue Date : 8/01/2025
Print Date : 8/01/2025

Sample Description Clients Ref : "Honeycomb Shades (Duette + Arena) Unix/Riley 10mm Blockout"
Honeycomb blind textiles
Colour : Black/White
End Use : Blinds
Nominal Composition : 100% Spun bonded Polyester
Nominal Mass per Unit Area/Density : 324g/m2
Nominal Thickness : 0.17mm



339609

73704

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Hunter Douglas Limited
338 Victoria Road
Rydalmere NSW 2116

Test Number : 24-004243
Issue Date : 8/01/2025
Print Date : 8/01/2025

AS 1530.2-1993

Methods for Fire Tests on Building Materials, Components and Structures.

Part 2: Test for Flammability of Materials

Date Tested	07-01-2025	
Selected Flammability Index	66	
	Length	Width
Spread Factor	40	40
Speed Factor	53	54
Heat Factor	13	11
Maximum height (d)		
Mean	21.0	21.0
Coefficient of Variation	0.0	0.0 %
Time		
Mean	17.8	16.3
Coefficient of Variation	2.3	3.2 %
Heat (a)		
Mean	53.2	47.2
Coefficient of Variation	9.8	10.4 %
Number of Specimens Tested	6	6

Tested as received.

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

339609

73704

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR