

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Hunter Douglas Limited
338 Victoria Road
Rydalmere NSW 2116

Test Number : 24-004508
Issue Date : 21/01/2025
Print Date : 21/01/2025

Sample Description Clients Ref : "Honeycomb Shades (Duette + Arena) Esprit/Haze)"
Honeycomb blind textile
Colour : White/Grey
End Use : Blinds
Nominal Composition : 100% Spun bonded Polyester
Nominal Mass per Unit Area/Density : 288g/m2
Nominal Thickness : 0.25mm



340652

73988

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

A handwritten signature in blue ink, appearing to read 'Fiona McDonald'.

Fiona McDonald

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Hunter Douglas Limited
338 Victoria Road
Rydalmere NSW 2116

Test Number : 24-004508
Issue Date : 21/01/2025
Print Date : 21/01/2025

AS 1530.2-1993

Methods for Fire Tests on Building Materials, Components and Structures. Part 2: Test for Flammability of Materials

| | | |
|-----------------------------|------------|--------|
| Date Tested | 17-01-2025 | |
| Selected Flammability Index | 24 | |
| | Length | Width |
| Spread Factor | 22 | 20 |
| Heat Factor | 2 | 2 |
| Maximum height (d) | | |
| Mean | 12.8 | 11.8 |
| Coefficient of Variation | 24.4 | 21.1 % |
| Heat (a) | | |
| Mean | 8.5 | 6.7 |
| Coefficient of Variation | 36.4 | 21.0 % |
| Number of Specimens Tested | 9 | 9 |

Visible smoke, melting, flaming debris

Tested as received.

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

340652

73988

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR